

**LASER 70 GSM type "6" – SUPERTACK -  
KRAFT 80GSM**

Issue: 11/03/2013  
Modification:4  
page 1/1

**GENERAL PRODUCT CHARACTERISTICS**

Total weight	170 gsm ± 5%	ISO 536
Total caliper	174 µm ± 6%	ISO 534

**FACE**

White woodfree uncoated paper, with good opacity and smoothness

Substance	70 gsm ± 3	ISO 536
Caliper	77 µm ± 3	ISO 534

**ADHESIVE**

Water emulsion acrylic based Supertack type, high initial tack and strong permanent bond for general use. Recommended on a wide variety of substrates, including paper, board, glass, steel

Peel adhesion	16.5/inch ± 2	FINAT1
Shear test	4h ± 2	FINAT8
Quick stick	14.4 N/inch ± 4	FINAT9
Min. application temp.	+5°C /+40°C	
Service temp. Range	-20°C/+90°C	

**BACKING**

One-side coated white kraft, solventless silicon coated

Substance	80 gsm ± 3	ISO 536
Caliper	82 µm ± 5	ISO 534

**SAFETY REGULATIONS**

- The self-adhesive product meets the European Standard EN71-3:2013 "Safety of Toys" - Migration of certain elements
- The adhesive coating meets the FDA 21 CFR 175.105 for contact with foodstuffs

**APPLICATIONS**

Information labeling for laser, ink-jet printers and photocopy machines. Office and retail use.

Trials are recommended, by the purchaser, on the intended substrates, prior to use, for product suitability.

**PRINTABILITY**

Face: good printing results by all common print processes. Recommended for laser printing and ink-jet  
Backing: good printing results by all common print processes, in one or more colors.

**ON REQUEST**

- Material certified Forest Stewardship Council
- Splits on the release paper, standard spacing 38mm or customized

**SHELF LIFE AND USE**

One (1) year from delivery date when stored at the following conditions:

- Temperature +5°C/+35°C
- Relative Humidity 45% - 60%
- Store in a cool dry place
- Store away from heaters or direct sunlight or rain
- Keep the sheets flat, the reels piled
- Store in the original packaging, remove packaging just before use
- Material to be acclimatized at least 24 hrs to ambient conditions